



<b>WPSM800000A</b>
<b>WHITE PIGMENTED WATERBORNE ENAMEL 6000</b>

**Descriptive notes**

High quality white pigmented waterborne enamel for spray application. It can be used only for 2K catalyzed enamel. WPSM800000A.. it's thinked for "SOFT" surface Very High resistance to scratch with "Self Healing" properties



<b>Gloss Versions</b>	3-5							
-----------------------	-----	--	--	--	--	--	--	--

**USAGE**

<b>Suitable for</b>	Furniture	Design Objects	Craftsmen				
<b>Method of application</b>	Spray	Air mixing spray painting					

**MAIN PROPERTIES**

<b>Filling</b>	High	<b>Easy Application</b>	High
<b>Drying</b>	Low	<b>Yellowing Resistance</b>	High
		<b>Scratch Resistance</b>	High

**PREPARATION OF THE PRODUCT**

	Code	%	Descriptive notes
<b>Recommended thinner</b>	Acqua	5÷15	
<b>Other thinners</b>			
<b>Recommended hardener</b>	INUR0601	15	
<b>Other hardeners</b>			
<b>Accelerant.</b>			

CHEMICAL-PHYSICAL CHARACTERISTICS		APPLICATION CHARACTERISTICS		DRYING	
<b>Specific gravity (kg/l) ±0.03</b>	1.15	<b>N° of coats</b>	1	<b>Dust free (min)</b>	20-30
<b>Solids Content (%) ±1</b>	42	<b>Qty. per coat (g/m²)</b>	120÷130	<b>Touch dry (min)</b>	60÷120
<b>Viscosity DIN 6 (20°C)</b>	40"÷50"			<b>Stackable (h)</b>	24 or oven 4h

**Additional information:**

■ Sanding the substrate using 280÷320 sandpaper and clean the surface after sanding. ■ Store the product in room where the temperature does not fall below 5°C. ■ If properly stored, the shelf-life is 12 months. ■ During application, keep the product and the substrate at a temperature of at least 15°C. ■ The use of coating devices not in perfect order may cause major defects in the coating film. ■ Wash immediately after use the tools with water and detergent.

**WARNING**

Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee. In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.  
Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.

Revision n° 1	Revision Date	01/09/2022
---------------	---------------	------------

Printed:	01/09/2022
----------	------------